

Espuma de PVC 48



Densidad kg/m ³	ASTM D1622	kg/m ³	nominal	48
Resistencia a la compresión	ASTM D1621-10	MPa	average min-ave min-min	0,69 0,48 0,37
Modulo de compresión	ASTM D1621-10	MPa	average min-ave min-min	33 18 13
Resistencia a la rotura	ASTM D1623	MPa	average min-ave min-min	0,95 0,66 -
Modulo de rotura	ASTM D1623	MPa	average min-ave min-min	87 57 49
Resistencia al corte	ASTM C273	MPa	average min-ave min-min	0,55 0,49 0,40
Modulo de corte	ASTM C273	MPa	average min-ave min-min	16 12 10
Alargamiento de corte a la rotura	ASTM C273	%	average	9
Medidas estandar		mm		1270 2730 80